



BENZIPOX EA9 EPOXY FINISH

Two Pack Epoxy Mid-Sheen Finish

BENZIPOX EA9 EPOXY FINISH is a two pack epoxy finish designed for use as an intermediate or finishing coat for ferrous and non-ferrous metal such as mild steel, aluminium, stainless steel, galvanised iron and phenolic sheeting, under immersion and non-immersion services. It has outstanding resistance to aqueous solution and a wide range of industrial chemicals. An excellent high performance and economical coating for steel tank for storage of potable water, gasoline, palm oil, vegetable and animal oils.

Standard Packing : 5 litres

Technical Information

Mixing Ratio (By Volume) : 4 : 1 (Base : Hardener)
 Binder : Polyamide
 Finish : Mid Sheen
 Color : Assorted colors, refer BENZI High Performance Coating color card
 Thinner : Thinner
 Solid Content : 65% (by weight); 55% (by volume)
 Dry Film Thickness : 80 - 150 microns / coat
 Theoretical Coverage : 7 m² / litre / coat (DFT of 80 microns); 4 m² / litre / coat (DFT of 150 microns)
 No. of coats : Minimum 2 coats
 Touch Dry @ 30°C : 2 - 3 hours (depends on temperature and humidity)
 Recoating Interval : Minimum 20 hours
 Curing Time @ 30°C : 6 - 7 days
 Pot Life @ 30°C : 5 hours after mixing of Base and Hardener
 Shelf Life : Minimum 12 months if properly stored

Typical Painting System


Substrate	Primer (1 coat)	Intermediate (1 coat)	Topcoat (1 - 2 coats)
Ferrous Metal (Internal of Steel Tank / Silo)	BENZIPOX EA9 Red Oxide Primer	BENZIPOX EA9 Epoxy Finish	BENZIPOX EA9 Epoxy Finish (Interior)
Ferrous Metal	BENZIPOX EA9 Red Oxide Primer	BENZIPOX EA9 Epoxy Finish	BENZIPOX EA9 Epoxy Finish (Interior)
Non-Ferrous Metal	BENZIPOX EA9 Red Oxide Primer	BENZIPOX EA9 Epoxy Finish	BENZIPOX EA9 Epoxy Finish (Interior)

Application Methods

Brush / Roller : Recommended for small area and touch up such as stripe coating, weld-seams, edges, corner, rivets etc. Dilute up to 5% of Thinner if necessary.
 Conventional Air Spray : Dilute up to 10% of Thinner if necessary
 Airless Spray : If thicker coat in one application is required, airless spray application is recommended. Dilute up to 5% of Thinner if necessary
 Handling : Mix the Base and Hardener in correct ratio and stir the paint thoroughly until completely mixed before painting
 Clean Up : Clean all paint equipment with Thinner immediately after use

BENZIPOX EA9 EPOXY FINISH

Two Pack Epoxy Mid-Sheen Finish



Surface Preparation

Ferrous Metal Surface

For optimum performance, mild steel surface shall be abrasively blasted in accordance to Swedish Standard Sa 2.5. If abrasive blasting is impossible, mechanical cleaning to St 3 is essential. If oxidation occurred on the blasted steel before application of paint, it is necessary to reblast the steel. The surface must be dry and free from any abrasive residues, dirt, grease and other contaminants prior to painting.

Non-Ferrous Metal Surface

For new surface, thorough solvent degreasing to SSPC-SP1 is necessary. For old surface, it must be abraded to remove corrosion deposits. All surfaces must be dry and clean prior to painting.





Storage

Keep container tightly closed and in a secure upright position, store in a cool and shady place, do not expose directly to sunlight and extremes of temperature. Keep out of reach of children.

Safety, Health and Environment

Ensure good ventilation during painting, do not breathe vapour or spray mist. Keep doors and windows open during application and drying. It is advisable to wear mask and eyes protector while applying. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. In case of accidental ingestion, DO NOT INDUCE VOMITING, seek immediate medical advice. To remove splashes of paint from skin by using water and soap or skin care product. Do not empty paint into drains or water courses, dispose of any paint waste in accordance with the appropriate Environmental Quality Regulations.

Materials Safety Data Sheet (MSDS) is available upon request.

DANGER			
			
<p>Hazard Statement: Flammable liquid & vapour. May be fatal if swallowed & enters respiratory tract. Harmful if in contact with skin. May cause allergic or asthma symptoms or breathing difficulties if inhaled. May cause respiratory irritation & allergic skin reaction. Very toxic to aquatic life with long lasting effects.</p>			
<p>Precautionary Statement: Keep out of reach of children. Keep away from heat, sparks, open flames, hot surfaces. No smoking. Wear protective gloves, eyes protector, face protector. Store in a well-ventilated place. Keep container tightly closed. Dispose of contents & container in accordance with all local, national or international regulations.</p>			

Limitation of Liability

Liability of MCI Paint Sdn Bhd on any claim of any kind, including claims based upon negligence of MCI Paint Sdn Bhd, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim. In no event shall MCI Paint Sdn Bhd be liable for consequential or incidental damages.

BENZIPOX EA9 EPOXY FINISH

Two Pack Epoxy Mid-Sheen Finish



Disclaimer

The above information is given to the best of our knowledge based on laboratory tests and practical experiences. However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself. We reserve the right to change the given information without prior notice due to production refinements arising from continuing research and development, which may result in changes in the paint properties.



MCI PAINT SDN BHD (849155-P)

Lot 5189, Kawasan Perindustrian Balakong Jaya, 43300 Balakong, Selangor.

Tel: +603 8962 2788 Fax: +603 8962 2798 Website: www.mcipaint.com.my